



Green Laminated Glass

Laminated glass is two or more lites (pieces) of glass permanently bonded together with one or more plastic interlayers (PVB: polyvinyl butyral film) using heat and pressure. Laminated glass can be broken, but the fragments will tend to adhere to the plastic layer and remain largely intact, reducing the risk of injury.

Meet Standard: ASTM C1172-14
 EN 14449
 ISO 12543
 ANSI Z97.1

| Glass Thickness | | Makeup / Composition | VLT % | SHGC | Winter U-Factor |
|-----------------|--------|--|-------|------|-----------------|
| mm | inches | | | | |
| 6.76mm | 1/4" | 1/8" Green Glass + 0.030" Clear PVB + 1/8" Clear Glass | 82 | 0.65 | 1.00 |
| 6.76mm | 1/4" | 1/8" Green Glass + 0.030" Clear PVB + 1/8" Green Glass | 75 | 0.57 | 1.00 |
| 8.28mm | 5/16" | 1/8" Green Glass + 0.090" Clear PVB + 1/8" Green Glass | 75 | 0.56 | 0.96 |
| 8.28mm | 5/16" | 1/8" Green Glass + 0.090" Clear PVB + 1/8" Clear Glass | 81 | 0.64 | 0.96 |
| 10.76mm | 3/8" | 3/16" Green Glass + 0.030" Clear PVB + 3/16" Clear Glass | 78 | 0.59 | 0.65 |
| 12.76mm | 1/2" | 1/4" Green Glass + 0.030" Clear PVB + 1/4" Green Glass | 75 | 0.57 | 0.65 |
| 14.28mm | 9/16" | 1/4" Green Glass + 0.090" Clear PVB + 1/4" Clear Glass | 77 | 0.59 | 0.65 |

Visible Light Transmittance (VLT): The percentage of the visible spectrum (light) that is transmitted through the glass.

SHGC: The fraction of solar radiation admitted through the glass, both directly transmitted and absorbed and subsequently released inward. SHGC is expressed as a number between 0 and 1. The lower a glass solar heat gain coefficient; the less solar heat it transmits.

Winter U- Value: Measure of the insulating characteristics of the glass in which how much heat gain or loss occur through the glass due to the difference of indoor and outdoor temperatures using NFRC winter nighttime environmental conditions of cold outside temperatures and no sunlight.

Hurricane Impact Resistant Glazing: To meet the requirements of the ASTM E 1996 Small Missile Test, laminated glasses typically include a PVB interlayer with a thickness of 0.06" (1.52 mm) and for the Large Missile Test an interlayer of 0.090" (2.28mm) is required.

Interglass cannot be held responsible for any deviation between the data introduced and the conditions on site. Technical specifications and other data are based on information available at the time of preparation of this document and are subject to change without notice. Data values were simulated using Optics 6 & used with Windows 5.2. The performance data is simulated, not actually measured