



Chemical Composition:

Silicon Dioxide (69% to 74%)
Calcium Oxide (5% to 14%)
Sodium Oxide (10% to 16%)
Magnesium Oxide (0% to 6%)
Aluminum Oxide (0% to 3%)
Other (0% to 5%)

Obscure 62/Crepe Patterned Glass

Description:

This pattern combines an attractive appearance with obscurity and light transmission capabilities, perfect. Also known as Nashiji, Dew or Crepe.

Key Features:

- Textured surface with patterns such as grids, dots, rhombuses, or stripes
- Light diffusion effect that blurs visibility while allowing light transmission
- Decorative and artistic appearance
- Available with single or double-sided patterns

Applications:

Ideal for a range of residential and commercial applications. Mostly used in jalousie windows and kitchen cabinet doors

Country of Origin: China

Manufacture: Jinjing

Meets Standards: ASTM C1036-11

Physical and Mechanical Properties

Characteristic	Symbol	Value and unit
Density	g/cm ³	2 5076
Knop hardness	Kgf/mm ²	456
Elasticity modulus	GPa	73.1
Rupture Modulus(Tensile Strength-ultimate)	Mpa	41.4
Transformation Temperature	Degree	556
Linear Coefficient of expansion between 20° Cand 300°	Degree	9.28 x10-6
Intenerate Temperature or Yield Point	Degree	606
Softening Point	Degree	710
High Temperature Viscosity log2	Degree	1392
High Temperature Viscosity log3	Degree	1152
Liquid Phase Temperature	Degree	1008

Glass Lite Tolerances (Stock Sheet Size)

Nominal Thickness	Thickness Tolerances	Dimension Tolerances
3 mm	±0.3mm	±4mm
4mm - 5 mm	±0.4mm	±4mm
6 mm - 10 mm	±0.5mm	±4mm